

PRODUCT DESCRIPTION:

**TWO COMPONENT EPOXY NOVALAK
POLYAMINE INTERMEDIATE COAT NMI780113.**

(CURING AGENT 4200109)

NMI EPOXY INTERMEDIATE 780113: is designed for use as a flat intermediate coat base on epoxy novalak and polyamine adduct resins and inert pigments with an excellent barrier efficiency in moderate and in door environment.

NMI EPOXY INTERMEDIATE 780113: can be applied as a top coat and mid coat in epoxy systems on primed surfaces.

Standard color availability Manufactured according RAL catalogue. When exposed to direct sun light in outdoor service become discolor and decrease of gloss.

GENERAL PROPERTIES :

Adhesion:	- Excellent to primed surfaces.
Corrosion Resistance:	- Excellent on correctly primed surfaces and high chemical resistance.
Temperature resistance:	-Dry: Maximum 160 °C. At service temperatures above 100°C/212°F, slight discoloration may be expected.

PHYSICAL PROPERTIES:

Colors/Shade No	Ral No.
Finish	Flat.
Volume Solid	70%
Theoretical spreading rate	7 m ² /liter 100Mic. Dft.
Flash point	35 °C
Specific gravity	1.45-1.55 kg/liter
V.O.C.	Max. 180 gr/liter
Shelf life	1 Years (25°C / 77°F) from time of production. Depending on storage condition, mechanical stirring may be necessary before usage.

MIXING:

Mixing ratio (by weight): Component A: 780113 Component: B 4200109

7.5

1

Pot life: 0.5 hours (20 °C/ 68 °F)

APPLICATION

Conditions Do not apply when relative humidity exceeds 80% or when the surface to be coated is less than 3 °C above the dew point.

Method Airless sprays Brush (touch-up)

Thinner (max. vol.) 30001 (10-30%) 3001 (5%)

Spray setting

Pump ratio minimum 30:1

Tip size 0.017" – 0.019"

Tip pressure 150 bar / 2200 Psi

(Airless spray data are indicative and subject to adjustment)

Cleaning of tools Thinner 3001

Indicated film thickness, dry 70 microns

Indicated film thickness, wet 100 microns

DRYING AND CURING TIMES AT (20 °C):

Dry to touch	Max.3 hour
Hard dry	Max.48 hours
Full curing	7 days
Recoat interval, min	24 hours
Recoat interval, max	7 days , see REMARKS

APPLICATION AND CURING CONDITIONS:

Primed surfaces	The surface must be completely clean and dry at the time of application, and its temperature must be above the dew point to avoid condensation. Minimum temperature for curing is 10°C/50°F. High humidity and/or condensation during application and the following 16 hours (20°C/68°F) may adversely affect the film formation. In confined spaces provide adequate ventilation during application and drying.
-----------------	--

REMARKS

PRECEDING COAT: Epoxy Polyamine Top Coat.

SUBSEQUENT COAT: None.

Film thickness: May be specified in another film thickness than indicated depending on purpose and area of use.

This will alter spreading rate and may influence drying time and recoating intervals.
Normal range is 100-150 microns/ 4 – 6 mils.

Thinning: The type and amount of thinner depend on application conditions, application method, temperature, ventilation, and substrate. Thinner 3001 is recommended in general.

Recoating intervals related to later conditions of temperature:
(100 micron/4 mils dry film thickness of NMI 780113)

Physical data versus temperatures:				
Surface temperature	5°C/41°F	10°C/50°F	20°C/68°F	30°C/86°F
Dry to touch approx.	16 hours	10 hours	6 hours	3 hours
Resist condensing humidity/ light showers after	4 days	2 days	24 hours	12 hours
Fully cured	20 days	14 days	7 days	5 days
Recoating interval with epoxy and polyurethane top coats	Min	24 hours	16 hours	8 hours
	Max	15 days	12 days	7 days
				5 days

A completely clean surface is mandatory to ensure intercoat adhesion, especially at long recoating intervals. Any dirt, oil, and grease have to be removed, e.g. with suitable detergent.

Salts to be removed by fresh water hosing. To check an adequate quality of the surface cleaning a test patch is recommended before actual recoating.

SAFETY:

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult RSI material safety data sheets and follow all local and national safety regulations. Harmful or fatal if swallowed; immediately seek medical assistance. Avoid inhalations of possible solvent vapors or paint mist, as well as paint contact with skin and eyes. Apply only on well-ventilated areas and ensure that adequate forced ventilation exists when applying paint in confined spaces or when the air is stagnant. Always take precautions against the risks of fire and explosions.

Issued: Sep 2016

NMI Paint Co.
Product data sheet 780113.

NMI **COATING**